



Daracote QD Bitumenliquid

Discussion

DARACOTE QD is a heavy duty, quick drying, solvent based, bitumen coating. DARACOTE QD is recommended for all types of metal coating applications where rust prevention is required, such as buried fence posts, inside gutters, truck and trailer under bodies or any other exposed metal work. DARACOTE QD is cost effective; its brush able qualities make it easy to use, with excellent adhesion on inferior substrates. The product is supplied in 5Lt. and 25Lt. drums and should be used within six months of the date indicated on the container. Thorough stirring is required before use.

Physical Properties

Colour:	Black
Application:	Brush roller or spray
Coverage:	5m ² /L
Total Solids:	+/- 55%
Specific Gravity:	+/- .09
Flash Point:	30 ^o c
Drying Time:	Does not dry but forms a non tacky film within 12 hours
Dilution:	Do not dilute.
Cleaning:	White spirits or mineral turpentine
Flammability:	Flammable when wet; observe all fire and ventilation precautions.

technical data sheet



Surface preparation

All forms of surface contamination must be removed to ensure a smooth surface, free of any loose material, or any other barrier to adhesion. Steel and galvanised steel surfaces must be free of loose paint, grease, grime, oil and rust.

Application

DARACOTE QD may be applied by brush, roller or spray. On non porous metal surfaces coverage will be about 5m²/L

DARACOTE QD is toxic in a wet state. Once a dry film has developed it has non tainting properties.

Deviation from the specified instructions will automatically invalidate any claim against non performance of the product, which in all circumstances, is restricted to replacement of product proven defective.

Technical assistance and applicator training are freely available to all approved users.