

# Daracryl Pinksaturator

## Discussion

PINK SATURATOR acrylic waterproofing compound is a highly flexible liquid applied emulsion, that when reinforced with stitch bonded polyester, forms a homogeneous seamless waterproofing system. The PINK SATURATOR compound is only used for the initial two saturating coats of the waterproofing system, for the final finishing coat DARACRYL ACRYLIC WATERPROOFING should be used. PINK SATURATOR in conjunction DARACRYL ACRYLIC WATERPROOFING and stitch bonded polyester is suitable for; flashings, parapet walls, properly graded roof decks, lap joints, roofing screws and many other waterproofing details. PINK SATURATOR is not suitable for areas of long term ponding or under tiles. PINK SATURATOR is available in 25L containers.

## Physical Properties

Colour:	Pink
Application:	Brush, roller or spray.
Coverage:	1.75L/m <sup>2</sup>
Total Solids:	+/- 55%
Specific Gravity:	+/- 1.2
Viscosity:	100 Krebbs Units at 25°C
Drying Time:	(Between Coats) Minimum 30 minutes at 25°C at 65% R.H. (Last Coat) 2-3 hours before resistant to rain. Full cure 12-20 hours at 25°C at 65% R.H.
Cleaning:	Water when wet. Ethyl acetate when dry.
Flammability:	Non Flammable

## Surface preparation

All forms of surface contamination must be removed to ensure a smooth surface, free of moisture and any loose material, or any other barrier to adhesion. Steel and galvanised steel surfaces must be free of loose paint, grease, grime, oil and rust.

Technical assistance and applicator training are freely available to all approved users.

## Application

### PRIMING:

All non metal surface – use a 50% PINK SATURATOR and clean water mix to prime the entire surface, allow a 30 minute drying time.

On metal surfaces – Prime with Darachem DC4 and allow 4 hour drying time.

Apply at the rate of 1L/m<sup>2</sup> undiluted PINK SATURATOR and immediately embed the SBP Geo-Fabric into the wet product ensuring no creases or folds in the material. Work the membrane into the PINK SATURATOR using a brush. Product should be evident “striking through” the membrane and if this is not the case, too little product has been applied or the product has been allowed to dry before embedding the membrane. At this point the bedding coat for the second run of membrane can be applied.

Apply the second run of membrane into the bedding coat in the same manner ensuring an additional coat at 1L/m<sup>2</sup> between the 2 layers of membrane at the 100 mm overlap.

Allow a minimum drying period of 30 minutes.

Apply a second coat PINK SATURATOR at the rate of .75L/m<sup>2</sup>. Allow a minimum of 30 minutes drying period.

Apply a final finishing coat of DARACRYL ACRYLIC WATERPROOFING at the rate of .75L/m<sup>2</sup>. It will be noted that a total of 2.5L/m<sup>2</sup> of PINK SATURATOR and DARACRYL ACRYLIC WATERPROOFING has now been applied. The minimum weight of the membrane alone shall be 100g/m<sup>2</sup>. The total weight per m<sup>2</sup> shall therefore be 1.5 kg

Note drying times are based on a temperature of 25<sup>0</sup> c min. and a R.H. of 60% max.

Technical assistance and applicator training are freely available to all approved users.

## Maintenance

A maintenance re-coat is recommended after three years.