



ck 86/23380/23. darachem house, 6 mission road, anderbolt, boksburg north.  
p.o. box 6008 dunswart 1508. tel: (011) 892 2917/8/9, fax: (011) 892 1519.  
email: info@darachem.co.za

# Daracryl Whitesaturator

## Discussion

WHITE SATURATOR acrylic waterproofing compound is a highly flexible liquid applied emulsion, that when reinforced with stitch bonded polyester, forms a homogeneous seamless waterproofing system. WHITE SATURATOR in conjunction with stitch bonded polyester is suitable for; flashings, parapet walls, properly graded roof decks, lap joints, roofing screws and many other waterproofing details. WHITE SATURATOR is not suitable for areas of long term ponding or under tiles. WHITE SATURATOR is available in 25L containers.

## Physical Properties

Colour:	White
Application:	Brush, roller or spray.
Coverage:	2.2L/m <sup>2</sup> – 2.5L/m <sup>2</sup> (depending on surface porosity)
Total Solids:	+/- 60%
Specific Gravity:	+/- 1.2
Viscosity:	100 Krebbs Units at 25°C
Drying Time:	(Between Coats) Minimum 30 minutes at 25°C at 65% R.H. (Last Coat) 2-3 hours before resistant to rain. Full cure 12-20 hours at 25°C at 65% R.H.
Cleaning:	Water when wet. Ethyl acetate when dry.
Flammability:	Non Flammable

technical data sheet



ck 86/23380/23. darachem house, 6 mission road, anderbolt, boksburg north.  
p.o. box 6008 dunswart 1508. tel: (011) 892 2917/8/9, fax: (011) 892 1519.  
email: info@darachem.co.za

## Surface preparation

All forms of surface contamination must be removed to ensure a smooth surface, free of moisture and any loose material, or any other barrier to adhesion. Steel and galvanised steel surfaces must be free of loose paint, grease, grime, oil and rust.

Technical assistance and applicator training are freely available to all approved users.

## Application

### PRIMING:

All non metal surface – use a 50% WHITE SATURATOR and clean water mix to prime the entire surface, allow a 30 minute drying time.

On metal surfaces – Prime with Darachem DC4 and allow 4 hour drying time.

Apply at the rate of 1L/m<sup>2</sup> undiluted WHITE SATURATOR and immediately embed the SBP Geo-Fabric into the wet product ensuring no creases or folds in the material. Work the membrane into the WHITE SATURATOR using a brush. Product should be evident “striking through” the membrane and if this is not the case, too little product has been applied or the product has been allowed to dry before embedding the membrane. At this point the bedding coat for the second run of membrane can be applied.

Apply the second run of membrane into the bedding coat in the same manner ensuring an additional coat at 1L/m<sup>2</sup> between the 2 layers of membrane at the 100 mm overlap.

After allowing a minimum drying period of 30 minutes.

Apply a second coat WHITE SATURATOR at the rate of .75L/m<sup>2</sup>. Allow a minimum of 30 minutes drying period.

Apply a further final coat of WHITE SATURATOR at the rate of .75L/m<sup>2</sup>. It will be noted that a total of 2.5L/m<sup>2</sup> of WHITE SATURATOR has now been applied. The minimum weight of the membrane alone shall be 100g/m<sup>2</sup>. The total weight per m<sup>2</sup> shall therefore be 1.5 kg

A decorative coating can be applied for colour matching purposes.

Note drying times are based on a temperature of 25<sup>0</sup> c min. and a R.H. of 60% max.

Technical assistance and applicator training are freely available to all approved users.

## Maintenance

A maintenance re-coat is recommended after three years.